

Plaslube® NY-1/TF/20 BK223

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		
Forms	<ul style="list-style-type: none"> Pellets 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.25		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	0.70	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	9000	psi	ASTM D638
Tensile Elongation (Break)	4.3	%	ASTM D638
Flexural Modulus	400000	psi	ASTM D790
Flexural Strength	14000	psi	ASTM D790
Compressive Strength	10000	psi	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.0	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	200	°F	ASTM D648
CLTE - Flow	4.6E-5	in/in/°F	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
