

Plaslube® PA6/6 GF30 TL10 BK

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 30% Filler by Weight
Additive	<ul style="list-style-type: none"> PTFE Lubricant
Features	<ul style="list-style-type: none"> Lubricated
Appearance	<ul style="list-style-type: none"> Black
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.45		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3 to 9.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.40E+6	psi	ASTM D638
Tensile Strength (Yield)	21000	psi	ASTM D638
Tensile Strength (Break)	20000	psi	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.5	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	490 to 530	°F
Middle Temperature	500 to 540	°F
Front Temperature	510 to 550	°F
Nozzle Temperature	520 to 560	°F
Processing (Melt) Temp	500 to 560	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow-Moderate	

Notes

¹ Typical properties: these are not to be construed as specifications.

