

Plaslube® PA6/6 CF30 TL15 HS BK

Techmer Polymer Modifiers - Polyamide 66

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer • PTFE Lubricant: 15%
Features	• Heat Stabilized • Lubricated • Low Friction • Wear Resistant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.48	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	28000	psi	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Flexural Modulus	1.98E+6	psi	ASTM D790
Flexural Strength	41500	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.10		
vs. Steel - Static	0.090		
Wear Factor	8.0	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.0	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	498	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	488	°F	ASTM D648
CLTE - Flow	1.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	10 to 1.0E+4	ohms·cm	ASTM D257
Additional Information	Nominal Value	Unit	Test Method
Limiting Pressure Velocity	• 30000.010 fpm • 44000.0100 fpm • 22000.01000 fpm	psi-ft/min	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	520 to 580	°F



Processing (Melt) Temp	540 to 580 °F
Mold Temperature	175 to 220 °F
Injection Rate	Slow-Moderate
Back Pressure	0.00 to 50.0 psi

Injection Notes

Screw Speed: Slow

Recommendations for Molding and Tool Conditions: Well vented mold

Moisture Content, as received: Product is packaged at 0.2% or less.

Notes

¹ Typical properties: these are not to be construed as specifications.

