

**Plaslube® PA6/6 GF30 TL5**

 Techmer Polymer Modifiers - *Polyamide 66*
**General Information**

General	
Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer • PTFE Lubricant: 5%
Features	• Heat Stabilized • Lubricated • Low Friction • Wear Resistant
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.40		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.70	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	23600	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.30E+6	psi	ASTM D790
Flexural Strength	36100	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.25		
vs. Steel - Static	0.18		
Wear Factor	35	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.1	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	118		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	498	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	480	°F	ASTM D648
CLTE - Flow	2.0E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	500	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	520 to 580	°F



Processing (Melt) Temp	540 to 580 °F
Mold Temperature	175 to 220 °F
Injection Rate	Slow-Moderate
Back Pressure	0.00 to 50.0 psi

#### Injection Notes

Screw Speed: Slow  
Recommendations for Molding and Tool Conditions: Well vented mold  
Moisture Content, as received: Product is packaged at 0.2% or less.

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

