

Plaslube® PA6/6 GF40 TL10

 Techmer Polymer Modifiers - *Polyamide 66*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Glass Fiber, 40% Filler by Weight
Additive	<ul style="list-style-type: none"> Heat Stabilizer PTFE Lubricant: 10%
Features	<ul style="list-style-type: none"> Heat Stabilized Lubricated
Appearance	<ul style="list-style-type: none"> Colors Available
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.56		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	26200	psi	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	1.50E+6	psi	ASTM D790
Flexural Strength	44000	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.25		
vs. Steel - Static	0.18		
Wear Factor	35	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.7	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	24	ft·lb/in	ASTM D4812
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	499	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	491	°F	ASTM D648
CLTE - Flow	1.1E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	500	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	520 to 580	°F



Processing (Melt) Temp	540 to 580 °F
Mold Temperature	175 to 220 °F
Injection Rate	Slow-Moderate
Back Pressure	0.00 to 50.0 psi

Injection Notes

Screw Speed: Slow

Recommendations for Molding and Tool Conditions: Well vented mold

Moisture Content, as received: Product is packaged at 0.2% or less.

Notes

¹ Typical properties: these are not to be construed as specifications.

