

**Radilon® A RV150W 100 NT**

 Radici Group High Performance Polymers - *Polyamide 66*
**General Information**
**Product Description**

PA66 15% glass fiber reinforced injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring improved stiffness and excellent heat ageing properties retention.

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Asia Pacific • Europe • Latin America • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Heat Stabilizer
Features	• Good Stiffness • Heat Aging Resistant • Heat Stabilized
Uses	• Automotive Applications
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• GM GMW3038P-PA66-GF15H • GM GMW3038P-PA66-GF15J • STELLANTIS MS-DB-41 CPN2125
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-T GF15

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.23	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>				ISO 294-4
Across Flow	0.90	--	%	
Flow	0.40	--	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	7.9	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	2.3	--	%	ISO 62
<b>Mechanical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	841000	--	psi	ISO 527-1/1A/1
Tensile Stress (Break)	18100	--	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.9	--	%	ISO 527-2/1A/5
Flexural Modulus <sup>3</sup>	783000	--	psi	ISO 178
Flexural Stress <sup>3</sup>	28300	--	psi	ISO 178
<b>Impact</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength (73°F)	3.1	--	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	19	--	ft·lb/in <sup>2</sup>	ISO 179/1eU
<b>Thermal</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (66 psi, Unannealed)	464	--	°F	ISO 75-2/Bf
Deflection Temperature Under Load (264 psi, Unannealed)	419	--	°F	ISO 75-2/Af
Vicat Softening Temperature	473	--	°F	ISO 306/B50
Melting Temperature <sup>4</sup>	500	--	°F	ISO 11357-3
<b>Electrical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity <sup>5</sup>	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity <sup>5</sup>	1.0E+15	1.0E+13	ohms·cm	IEC 62631-3-1
<b>Flammability</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795



Flame Rating (0.031 in)	HB	--	UL 94
Glow Wire Flammability Index (0.08 in)	1200	--	°F IEC 60695-2-12

### Processing Information

Injection	Dry Unit
Drying Temperature - Desiccant Dryer	176 °F
Drying Time - Desiccant Dryer	2.0 to 4.0 hr
Dew Point - Desiccant Dryer	< -4 °F
Suggested Max Moisture	0.15 %
Processing (Melt) Temp	536 to 572 °F
Mold Temperature	176 to 212 °F
Injection Rate	Moderate

### Notes

- <sup>1</sup> Typical properties: these are not to be construed as specifications.
- <sup>2</sup> 300°C Melt Temperature/ 90°C Mold Temperature/ 60 MPa Cavity Pressure
- <sup>3</sup> 0.079 in/min
- <sup>4</sup> 10°C/min
- <sup>5</sup> 500V

