

Radilon® A RV350K 100 NT

 Radici Group High Performance Polymers - *Polyamide 66*
General Information
Product Description

PA66 35% glass fiber reinforced injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring high stiffness, good mechanical resistance and good heat ageing properties retention.

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Aging Resistant • Heat Stabilized • High Stiffness
Uses	• Automotive Applications
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• GM GMW3038P-PA66-GF35H • IMDS ID 111141375 Color: 100 Natural
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-T GF35

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.40	--	g/cm ³	ISO 1183
Molding Shrinkage ²				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.30	--	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	6.3	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	1.5	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.60E+6	1.44E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	28300	18900	psi	ISO 527-2/1A/5
Tensile Strain (Break)	4.0	4.5	%	ISO 527-2/1A/5
Flexural Modulus ³	1.42E+6	--	psi	ISO 178
Flexural Stress ³	42800	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	4.8	--	ft·lb/in ²	
73°F	6.7	8.1	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	43	--	ft·lb/in ²	
73°F	48	50	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	482	--	°F	ISO 75-2/Bf
Deflection Temperature Under Load (264 psi, Unannealed)	455	--	°F	ISO 75-2/ Af
Vicat Softening Temperature	482	--	°F	ISO 306/B50
Melting Temperature ⁴	500	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method



Surface Resistivity ⁵	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity ⁵	1.0E+15	1.0E+13	ohms·cm	IEC 62631-3-1
Comparative Tracking Index (Solution A)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index (0.08 in)	1290	--	°F	IEC 60695-2-12

Processing Information

Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 212	°F
Injection Rate	Moderate-Fast	

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 300°C Melt Temperature/ 90°C Mold Temperature/ 60 MPa Cavity Pressure
- ³ 0.079 in/min
- ⁴ 10°C/min
- ⁵ 500V

