

Radilon® A RV430K 1700 NT

 Radici Group High Performance Polymers - *Polyamide 66*

General Information

Product Description

PA66 43% glass fiber reinforced injection moulding grade, natural colour

Suitable for parts requiring high stiffness and good impact resistance

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 43% Filler by Weight
Features	• Good Impact Resistance • High Stiffness
Uses	• Automotive Applications
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Automotive Specifications	• STELLANTIS MS-DB-41 CPN3810
Appearance	• Black
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-GF43

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183
Molding Shrinkage ²			ISO 294-4
Across Flow	0.90	%	
Flow	0.30	%	
Water Absorption (Saturation, 73°F, 0.0787 in)	5.3	%	ISO 62
Water Absorption (Equilibrium, 73°F, 0.0787 in, 50% RH)	1.2	%	ISO 62
Viscosity Index - Sulfuric Acid	3880	in ³ /lb	ISO 307
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.89E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	31900	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	%	ISO 527-2/1A/5
Flexural Modulus ³	1.71E+6	psi	ISO 178
Flexural Stress ³	45500	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	4.8	ft·lb/in ²	
73°F	7.6	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	29	ft·lb/in ²	
73°F	40	ft·lb/in ²	
Notched Izod Impact Strength (73°F)	7.2	ft·lb/in ²	ISO 180/1A
Unnotched Izod Impact Strength (73°F)	36	ft·lb/in ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	491	°F	ISO 75-2/Bf
Deflection Temperature Under Load (264 psi, Unannealed)	469	°F	ISO 75-2/Af
Vicat Softening Temperature	469	°F	ISO 306/B50
Melting Temperature ⁴	500	°F	ISO 11357-3



Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.10	%
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 212	°F
Injection Rate	Moderate-Fast	

Notes

- ¹ Typical properties: these are not to be construed as specifications.
- ² 300°C Melt Temperature/ 90°C Mold Temperature/ 60 MPa Cavity Pressure
- ³ 0.079 in/min
- ⁴ 10°C/min

