

Starflam® 525K BK0778

Ascend Performance Materials Operations LLC - Polyamide 66

General Information
Product Description

Starflam 525K BK0778 is an organic heat stabilized, non-halogenated, non-red phosphorus flame retardant, PA66 grade modified with 25% glass fiber for improved stiffness and strength.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Additive	• Flame Retardant		
Features	• Corrosion Resistant	• Good Dimensional Stability	• High Flow
	• Fast Molding Cycle	• Good Processability	• High Strength
	• Flame Retardant	• Heat Aging Resistant	• Low Density
Automotive Specifications	• GM GMW18122P-PA-GF25-Type B1	• TESLA TM-1006 V3 303120V	
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID	• PA66-GF25 FR		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.40	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 73°F, 0.0787 in	1.1	%	
Flow : 73°F, 0.0787 in	0.30	%	
Water Absorption (24 hr, 73°F)	1.2	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	1.23E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	18400	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.7	%	ISO 527-2
Flexural Modulus (73°F)	1.32E+6	psi	ISO 178
Flexural Stress (73°F)	28000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-40°F	3.9	ft·lb/in ²	
-22°F	3.9	ft·lb/in ²	
73°F	4.2	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-40°F	26	ft·lb/in ²	
-22°F	27	ft·lb/in ²	
73°F	27	ft·lb/in ²	
Notched Izod Impact Strength			ISO 180/1A
-40°F	3.7	ft·lb/in ²	
-22°F	3.7	ft·lb/in ²	
73°F	3.9	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	493	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	459	°F	ISO 75-2/A
Melting Temperature	500	°F	ISO 11357-3



CLTE - Flow (73 to 131°F, 0.0787 in)	1.3E-5 in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	3.7E-5 in/in/°F	ISO 11359-2
RTI Elec		UL 746B
0.0079 in	284 °F	
0.016 in	284 °F	
0.030 in	284 °F	
0.06 in	284 °F	
0.12 in	284 °F	
RTI Imp		UL 746B
0.0079 in	203 °F	
0.016 in	230 °F	
0.030 in	248 °F	
0.06 in	266 °F	
0.12 in	266 °F	
RTI Str		UL 746B
0.0079 in	239 °F	
0.016 in	266 °F	
0.030 in	284 °F	
0.06 in	302 °F	
0.12 in	302 °F	

Electrical	Nominal Value	Unit	Test Method
Electric Strength (0.0394 in)	1100	V/mil	IEC 60243-1
Comparative Tracking Index (0.118 in)	600	V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.016 in	PLC 0		
0.030 in	PLC 0		
0.06 in	PLC 0		
0.12 in	PLC 0		
Hot-wire Ignition (HWI)			UL 746A
0.016 in	PLC 2		
0.030 in	PLC 1		
0.06 in	PLC 0		
0.12 in	PLC 0		

Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.0079 in	V-0		
0.016 in	V-0		
0.030 in	V-0		
0.06 in	• • V-0 5VA		
0.12 in	• • V-0 5VA		
Glow Wire Flammability Index			IEC 60695-2-12
0.0079 in	1760	°F	
0.016 in	1760	°F	
0.030 in	1760	°F	
0.06 in	1760	°F	
0.12 in	1760	°F	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	4.0 to 6.0	hr
Rear Temperature	527 to 572	°F
Middle Temperature	527 to 572	°F
Front Temperature	527 to 572	°F
Processing (Melt) Temp	527 to 572	°F
Mold Temperature	140 to 248	°F

