

Starflam® 525H NT0767

Ascend Performance Materials Operations LLC - Polyamide 66

General Information
Product Description

Starflam 525H NT0767 is a heat stabilized, non-red phosphorus and non-halogenated flame retardant, PA66 grade modified with 25% glass fiber for improved stiffness and strength.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Additive	• Flame Retardant		
Features	• Corrosion Resistant • Fast Molding Cycle • Flame Retardant	• Good Colorability • Good Dimensional Stability • Good Processability	• Heat Aging Resistant • High Flow • High Strength
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID	• PA66-GF25 FR		

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.40	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.1	--	%	
Flow : 73°F, 0.0787 in	0.30	--	%	
Water Absorption (24 hr, 73°F)	1.3	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.9	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	1.33E+6	1.06E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	19700	14100	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.2	3.4	%	ISO 527-2
Flexural Modulus (73°F)	1.31E+6	885000	psi	ISO 178
Flexural Stress (73°F)	30500	18900	psi	ISO 178
Poisson's Ratio (73°F)	0.34	--		ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-40°F	4.4	4.6	ft·lb/in ²	
-22°F	4.5	4.6	ft·lb/in ²	
73°F	5.2	6.2	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-40°F	32	31	ft·lb/in ²	
-22°F	32	32	ft·lb/in ²	
73°F	32	35	ft·lb/in ²	
Notched Izod Impact Strength				ISO 180/1A
-40°F	4.3	4.3	ft·lb/in ²	
-22°F	4.2	4.4	ft·lb/in ²	
73°F	4.7	5.7	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	495	489	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	457	442	°F	ISO 75-2/A
Melting Temperature	500	--	°F	ISO 11357-3



CLTE - Flow (73 to 131°F, 0.0787 in)	1.1E-5	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	3.8E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746B
0.0079 in	284	--	°F	
0.016 in	302	--	°F	
0.030 in	302	--	°F	
0.06 in	302	--	°F	
0.12 in	302	--	°F	
RTI Imp				UL 746B
0.0079 in	230	--	°F	
0.016 in	239	--	°F	
0.030 in	266	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
RTI Str				UL 746B
0.0079 in	248	--	°F	
0.016 in	257	--	°F	
0.030 in	284	--	°F	
0.06 in	302	--	°F	
0.12 in	302	--	°F	
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0394 in)	2.1E+15	--	ohms·cm	IEC 60093
Electric Strength (0.0394 in)	990	480	V/mil	IEC 60243-1
Comparative Tracking Index (0.118 in)	575	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.016 in	PLC 0	--		
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
Hot-wire Ignition (HWI)				UL 746A
0.016 in	PLC 1	--		
0.030 in	PLC 1	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.0079 in	V-0	--		
0.016 in	V-0	--		
0.030 in	V-0	--		
0.06 in	<ul style="list-style-type: none"> • V-0 • 5VA 	--		
0.12 in	<ul style="list-style-type: none"> • V-0 • 5VA 	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.016 in	1760	--	°F	
0.030 in	1760	--	°F	
0.06 in	1760	--	°F	
0.12 in	1760	--	°F	
Glow Wire Ignition Temperature (0.016 in)	1380	--	°F	IEC 60695-2-13
Oxygen Index ²	34	--	%	ISO 4589-2
Smoke Density ²	130	--	Ds	ISO 5659-2
Smoke Toxicity ²	0.38	--	CIT NLP	NF X 70-100-1/2

Processing Information

Injection	Dry Unit
Drying Temperature	176 °F
Drying Time	4.0 to 6.0 hr
Barrel Temperature	527 to 572 °F
Temperature	527 to 572 °F
Temperature	527 to 572 °F
(Melt) Temp	527 to 572 °F
Temperature	140 to 248 °F