

**Vydyne® A 30 GB NT KW2**

 Ascend Performance Materials Operations LLC - *Polyamide 66*
**General Information**
**Product Description**

Vydyne A 30 GB NT KW2 is standard flow, organic heat stabilized, 30% glass-beads reinforced PA66 resin. Available in natural, this product is also lubricated for improved machine feed and flow. Glass-beads provide the molded parts with good surface finish and low warpage.

**General**

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Bead, 30% Filler by Weight
Additive	• Heat Stabilizer • Lubricant
Features	• Chemical Resistant • Good Dimensional Stability • Heat Stabilized • Gasoline Resistant • Good Flow • Heat Stabilized - Organic • General Purpose • Good Heat Resistance • Lubricated
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID	• PA66-GB30

**Properties <sup>1</sup>**

Physical	Dry	Conditioned	Unit	Test Method
Density	1.35	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	1.2	--	%	
Flow : 73°F, 0.0787 in	1.0	--	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	1.7	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	653000	363000	psi	ISO 527-1
Tensile Stress (Break, 73°F)	11600	7980	psi	ISO 527-2
Tensile Strain (Break, 73°F)	5.0	12	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength (73°F)	1.9	3.8	ft-lb/in <sup>2</sup>	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	446	--	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	239	--	°F	ISO 75-2/A
Melting Temperature	500	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (0.118 in)	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.0787 in)	4.0	--	in/min	ISO 3795
Flame Rating				UL 94
0.06 in	HB	--		
0.12 in	HB	--		

**Processing Information**

Injection	Dry Unit
Drying Temperature	185 to 203 °F
Drying Time	> 3.0 hr
Rear Temperature	500 to 554 °F
Middle Temperature	500 to 554 °F
Front Temperature	500 to 554 °F



Nozzle Temperature	500 to 554 °F
Processing (Melt) Temp	500 to 554 °F
Mold Temperature	158 to 194 °F

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

