

## Vydyne® LUB A 30 FC BK TF2

Ascend Performance Materials Operations LLC - Polyamide 66

### General Information

#### Product Description

Vydyne LUB A 30 FC BK TF2 is standard flow 30% carbon-fiber reinforced, 10% PTFE lubricated PA66 resin. Available in black, it is specifically designed for high stiffness and strength. This product also has a low coefficient of friction and is electrically conductive.

#### General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight
Additive	• Lubricant • Slip
Features	• Abrasion Resistant • General Purpose • High Tensile Strength • Chemical Resistant • Good Flow • Lubricated • Gasoline Resistant • Good Stiffness • Slip
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding
Resin ID	• PA66-CF30

### Properties <sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.35	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.50	--	%	
Flow : 73°F, 0.0787 in	0.10	--	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	1.8	--	%	ISO 62
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (73°F)	2.90E+6	2.15E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	32600	26100	psi	ISO 527-2
Tensile Strain (Break, 73°F)	1.5	3.0	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength (73°F)	4.0	5.2	ft·lb/in <sup>2</sup>	ISO 180/1A
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	482	--	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	473	--	°F	ISO 75-2/A
Melting Temperature	500	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Volume Resistivity (0.0394 in)	1.0E+4	--	ohms·cm	IEC 60093
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.06 in	HB	--		
0.12 in	HB	--		

### Processing Information

Injection	Dry Unit
Drying Temperature	194 to 230 °F
Drying Time	> 3.0 hr
Rear Temperature	518 to 536 °F
Middle Temperature	518 to 563 °F
Front Temperature	518 to 563 °F
Nozzle Temperature	518 to 563 °F



Processing (Melt) Temp	518 to 563 °F
Mold Temperature	158 to 194 °F

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

