

**Vydyne® R533H BK02**

 Ascend Performance Materials Operations LLC - *Polyamide 66*
**General Information**
**Product Description**

Vydyne R533H BK02 is a general purpose, 33% glass-filled, heat-stabilized PA66 based resin designed for injection molding applications. R533H BK02 offers improved flow with a black surface finish and maintains the excellent resistance typical of PA66 in chemicals, machine and motor oils, solvents, and gasoline.

**General**

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 33% Filler by Weight		
Additive	• Heat Stabilizer	• Lubricant	
Features	• Good Mold Release	• High Rigidity	• Lubricated
	• Heat Stabilized	• High Strength	
	• High Flow	• Hydrolysis Resistant	
Agency Ratings	• ASTM D4066 PA012G35	• ASTM D6779 PA012G35	• SAE J1639 PA1116
Automotive Specifications	• AISIN TO20141124 - P-PA66-GF33-805	• APTIV M4692V	• TOYOTA TSM 5603G Color: Class 2B, Rev 5
UL File Number	• E70062		
Appearance	• Black		
Forms	• Pellets		
Processing Method	• Injection Molding		
Resin ID	• PA66-GF33		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Density	1.40	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow : 73°F, 0.0787 in	0.90	--	%	
Flow : 73°F, 0.0787 in	0.40	--	%	
Water Absorption (24 hr, 73°F)	0.80	--	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	1.7	--	%	ISO 62
Outdoor Suitability	f1	--		UL 746C
<b>Mechanical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus (73°F)	1.54E+6	1.16E+6	psi	ISO 527-1
Tensile Stress (Break, 73°F)	29700	21000	psi	ISO 527-2
Tensile Strain (Break, 73°F)	3.0	4.7	%	ISO 527-2
Flexural Modulus (73°F)	1.52E+6	1.04E+6	psi	ISO 178
Flexural Stress (73°F)	42400	29000	psi	ISO 178
Poisson's Ratio (73°F)	0.40	--		ISO 527-2
<b>Impact</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Charpy Notched Impact Strength				ISO 179/1eA
-40°F	5.7	5.2	ft·lb/in <sup>2</sup>	
-22°F	5.2	5.2	ft·lb/in <sup>2</sup>	
73°F	6.2	8.1	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-40°F	34	36	ft·lb/in <sup>2</sup>	
-22°F	32	36	ft·lb/in <sup>2</sup>	
73°F	39	47	ft·lb/in <sup>2</sup>	
Notched Izod Impact Strength				ISO 180/1A
-40°F	5.2	5.2	ft·lb/in <sup>2</sup>	



-22°F	5.2	5.2	ft·lb/in <sup>2</sup>	
73°F	5.7	7.1	ft·lb/in <sup>2</sup>	
<b>Thermal</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (66 psi, Unannealed)	502	498	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	480	473	°F	ISO 75-2/A
Melting Temperature	504	--	°F	ISO 11357-3
CLTE - Flow (73 to 131°F, 0.0787 in)	8.9E-6	--	in/in/°F	ISO 11359-2
CLTE - Transverse (73 to 131°F, 0.0787 in)	4.0E-5	--	in/in/°F	ISO 11359-2
RTI Elec				UL 746B
0.030 in	284	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
RTI Imp				UL 746B
0.030 in	257	--	°F	
0.06 in	257	--	°F	
0.12 in	257	--	°F	
RTI Str				UL 746B
0.030 in	284	--	°F	
0.06 in	284	--	°F	
0.12 in	284	--	°F	
<b>Electrical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Volume Resistivity (0.0394 in)	1.0E+13	--	ohms·cm	IEC 60093
Electric Strength (0.0394 in)	1000	860	V/mil	IEC 60243-1
Arc Resistance (0.118 in)	PLC 6	--		ASTM D495
Comparative Tracking Index (0.118 in)	250 to 399	--	V	IEC 60112
High Amp Arc Ignition (HAI)				UL 746A
0.030 in	PLC 0	--		
0.06 in	PLC 0	--		
0.12 in	PLC 0	--		
High Voltage Arc Tracking Rate (HVTR) (0.118 in)	PLC 1	--		UL 746A
Hot-wire Ignition (HWI)				UL 746A
0.030 in	PLC 4	--		
0.06 in	PLC 3	--		
0.12 in	PLC 4	--		
<b>Flammability</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating				UL 94
0.030 in	HB	--		
0.06 in	HB	--		
0.12 in	HB	--		
Glow Wire Flammability Index				IEC 60695-2-12
0.030 in	1340	--	°F	
0.06 in	1290	--	°F	
0.12 in	1610	--	°F	
Glow Wire Ignition Temperature				IEC 60695-2-13
0.030 in	1380	--	°F	
0.06 in	1340	--	°F	
0.12 in	1380	--	°F	

### Processing Information

<b>Injection</b>	<b>Dry Unit</b>
Drying Temperature	176 °F
Drying Time	4.0 hr
Rear Temperature	536 to 590 °F
Middle Temperature	536 to 590 °F
Front Temperature	536 to 590 °F
Nozzle Temperature	536 to 590 °F
Processing (Melt) Temp	545 to 581 °F
Mold Temperature	149 to 203 °F

