

HiFill® PA6/10 BK

Techmer Polymer Modifiers - *Polyamide 610*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.07		ASTM D792
Water Absorption (24 hr)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8700	psi	ASTM D638
Tensile Elongation (Yield)	100	%	ASTM D638
Flexural Modulus	290000	psi	ASTM D790
Flexural Strength	11000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.90	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	347	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	151	°F	ASTM D648
CLTE - Flow	4.4E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

