

**Plaslube® PA6/10 GF30 TS15**

 Techmer Polymer Modifiers - *Polyamide 610*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber
Additive	• PTFE + Silicone Lubricant
Features	• Lubricated • Wear Resistant
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.43		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.16	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength (Break)	17000	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	1.10E+6	psi	ASTM D790
Flexural Strength	28300	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.23		
vs. Steel - Static	0.18		
Wear Factor	9.0	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (73°F, 0.125 in)	2.1	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	16	ft·lb/in	ASTM D4812
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (264 psi, Unannealed)	405	°F	ASTM D648
CLTE - Flow	1.5E-5	in/in/°F	ASTM D696
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating	HB		UL 94

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
