

**HiFill® PA6/10 GF50 L**

 Techmer Polymer Modifiers - *Polyamide 610*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>
Filler / Reinforcement	<ul style="list-style-type: none"> <li>Glass Fiber, 50% Filler by Weight</li> </ul>
Additive	<ul style="list-style-type: none"> <li>Lubricant</li> </ul>
Features	<ul style="list-style-type: none"> <li>Lubricated</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Colors Available</li> </ul>
Forms	<ul style="list-style-type: none"> <li>Pellets</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.50		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength (Break)	27000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.90E+6	psi	ASTM D790
Flexural Strength	39000	psi	ASTM D790
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (73°F, 0.125 in)	2.6	ft·lb/in	ASTM D256
<b>Thermal</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (264 psi, Unannealed)	425	°F	ASTM D648
CLTE - Flow	8.5E-6	in/in/°F	ASTM D696
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	440	V/mil	ASTM D149
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating (0.06 in)	HB		UL 94

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
