

InLube® PA610GF35TF5

Americhem - Polyamide 610

General Information

Product Description

35% GLASS FIBER REINFORCED 5% PTFE LUBRICATED NYLON 610

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight		
Additive	• PTFE Lubricant: 5%		
Features	• Chemical Resistant • Filled • Good Dimensional Stability	• Good Mold Release • High Stiffness • High Strength	• Low Friction • Lubricated • Wear Resistant
Uses	• Closures • Consumer Applications • Electrical/Electronic Applications	• Engineering Parts • Household Goods • Industrial Applications	• Industrial Parts • Office Automation Equipment • Outdoor Applications
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.40		ASTM D792
Specific Volume	19.8	in ³ /lb	
Molding Shrinkage - Flow	3.0E-3 to 4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.18	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	23500	psi	ASTM D638
Tensile Elongation (Yield)	2.0 to 4.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	32000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	2.0	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	14	ft-lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	420	°F	ASTM D648
CLTE - Flow	1.5E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+17	ohms	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	175	°F
Drying Time	4.0	hr
Processing (Melt) Temp	460 to 525	°F
Mold Temperature	200	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm
Vent Depth	5.0E-4 to 1.0E-3	in

