

AuroraGuard™ 13819

Aurora Material Solutions, LLC - *Polybutylene Terephthalate*
General Information
Product Description

Medium Viscosity Polybutylene Terephthalate

Formerly known as EnCounter 13819

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Chemical Resistant	• Good Flow	• Medium Viscosity
	• Fast Molding Cycle	• High Gloss	
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.31		ASTM D792
Molding Shrinkage - Flow (0.126 in)	0.019 to 0.023	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8000	psi	ASTM D638
Tensile Elongation (Break)	90	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.80	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	250	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	120	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	460 to 490	°F
Middle Temperature	460 to 490	°F
Front Temperature	470 to 500	°F
Nozzle Temperature	460 to 490	°F
Processing (Melt) Temp	470 to 500	°F
Mold Temperature	120 to 170	°F

Injection Notes

Maximum Drying Time 8.0 hrs

Notes
¹ Typical properties: these are not to be construed as specifications.
