

AuroraGuard™ 125GF

Aurora Material Solutions, LLC - *Polybutylene Terephthalate*

General Information

Product Description

25% Glass Fiber Reinforced

Formerly known as EnCounter 125GF

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight		
Uses	• Automotive Applications • Business Equipment	• Electrical/Electronic Applications • Structural Parts	
Appearance	• Black	• Colors Available	• Natural Color
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.46		ASTM D792
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 8.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13500	psi	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	750000	psi	ASTM D790
Flexural Strength	21000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.99	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	410	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	376	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	460 to 490	°F
Middle Temperature	470 to 500	°F
Front Temperature	480 to 510	°F
Nozzle Temperature	470 to 500	°F
Processing (Melt) Temp	480 to 510	°F
Mold Temperature	150 to 190	°F
Injection Notes		
Maximum Drying Time 8 hrs		

