

DURANEX® CN7015NN/BB

 Polyplastics - *Polybutylene Terephthalate*
General Information
Product Description

Flame Retardant, Standard, UL Approved Regrind 50% Inclusive

GF15% Reinforced

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Regrind and Blending Performance
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT-GF15 FR(17)<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.59	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	14800	psi	ISO 527-2
Tensile Strain (Break)	2.3	%	ISO 527-2
Flexural Modulus	905000	psi	ISO 178
Flexural Stress	23100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.4	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	401	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	2.2E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	IEC 60093
Electric Strength (0.118 in)	460	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.
