

**DURANEX® CN7010NN/BB**

 Polyplastics - *Polybutylene Terephthalate*

## General Information

**Product Description**

Flame Retardant, Standard, UL Approved Regrind 50% Inclusive

GF10% Reinforced

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Regrind and Blending Performance
UL File Number	• E213445
Forms	• Pellets, Reprocessed
Part Marking Code (ISO 11469)	• >PBT-GF10FR(17)<

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.49	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	13100	psi	ISO 527-2
Tensile Strain (Break)	3.5	%	ISO 527-2
Flexural Modulus	682000	psi	ISO 178
Flexural Stress	20300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.4	ft·lb/in <sup>2</sup>	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	401	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	2.8E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	5.0E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	4.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.
