

**DURANEX® CRN7015GP**

 Polyplastics - *Polybutylene Terephthalate*

## General Information

**Product Description**

Flame Retardant, Low Gas Generation, Low Contact Contamination, UL Approved Regrind 50% Inclusive

GF15% Reinforced

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East      • Europe      • North America • Asia Pacific      • Latin America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant      • Regrind and Blending Performance
UL File Number	• E213445
Forms	• Pellets, Reprocessed
Part Marking Code (ISO 11469)	• >PBT-GF15FR(17)<

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.62	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	16100	psi	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	985000	psi	ISO 178
Flexural Stress	23900	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.6	ft·lb/in <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	392	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	2.2E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number	EF2001/ED3002		

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.
