

**DURANEX® 330LC**

 Polyplastics - *Polybutylene Terephthalate*

## General Information

**Product Description**

Low Oligomer Content, HB

GF30% Reinforced

**General**

Material Status	• Commercial: Active
Availability	• Africa & Middle East      • Europe      • North America • Asia Pacific      • Latin America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT-GF30<

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	20500	psi	ISO 527-2
Tensile Strain (Break)	3.2	%	ISO 527-2
Flexural Modulus	1.22E+6	psi	ISO 178
Flexural Stress	31200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	5.1	ft·lb/in <sup>2</sup>	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	406	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	1.1E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	5.0E-5	in/in/°F	Internal Method
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number	EF2001		

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.
