

DURANEX® 6370B

 Polyplastics - *Polybutylene Terephthalate*
General Information
Product Description

Low Warpage, Flame Retardant, Standard

GB30% Filled, Anisotropy Improved

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Bead, 30% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Low Warpage
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT-GB30 FR(17)<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.67	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	6820	psi	ISO 527-2
Tensile Strain (Break)	1.8	%	ISO 527-2
Flexural Modulus	632000	psi	ISO 178
Flexural Stress	12200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	0.90	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	65		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	194	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	3.9E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	3.9E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+15	ohms·cm	IEC 60093
Electric Strength (0.118 in)	380	V/mil	IEC 60243-1
Comparative Tracking Index	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	Test Method
Color Number	EF2001/ED3002		

Notes
¹ Typical properties: these are not to be construed as specifications.
