

HiFill® PBT 2110

 Techmer Polymer Modifiers - *Polybutylene Terephthalate*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Impact Modifier
Features	<ul style="list-style-type: none"> Impact Modified
Appearance	<ul style="list-style-type: none"> Colors Available
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.27		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.024	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical			
Nominal Value Unit Test Method			
Tensile Strength (Yield)	6000	psi	ASTM D638
Tensile Elongation (Break)	25	%	ASTM D638
Flexural Modulus	270000	psi	ASTM D790
Flexural Strength	9500	psi	ASTM D790
Impact			
Nominal Value Unit Test Method			
Notched Izod Impact (73°F, 0.125 in)	3.0	ft·lb/in	ASTM D256
Unnotched Izod Impact (73°F, 0.125 in)	3.0	ft·lb/in	ASTM D4812
Hardness			
Nominal Value Unit Test Method			
Rockwell Hardness (R-Scale)	104		ASTM D785
Thermal			
Nominal Value Unit Test Method			
Deflection Temperature Under Load (66 psi, Unannealed)	245	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	120	°F	ASTM D648
CLTE - Flow	4.8E-5	in/in/°F	ASTM D696
Electrical			
Nominal Value Unit Test Method			
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	400	V/mil	ASTM D149
Flammability			
Nominal Value Unit Test Method			
Flame Rating (0.13 in)	HB		UL 94

