

HiFill FR® PBT FR-DE RD131

 Techmer Polymer Modifiers - *Polybutylene Terephthalate*
General Information

General	
Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Flame Retardant
Features	<ul style="list-style-type: none"> Flame Retardant
Appearance	<ul style="list-style-type: none"> Red
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.25		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	293000	psi	ASTM D638
Tensile Strength (Yield)	7200	psi	ASTM D638
Tensile Strength (Break)	5400	psi	ASTM D638
Tensile Elongation (Break)	23	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.8	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	455 to 480	°F
Middle Temperature	465 to 490	°F
Front Temperature	475 to 500	°F
Nozzle Temperature	475 to 500	°F
Processing (Melt) Temp	475 to 525	°F
Mold Temperature	110 to 150	°F
Injection Rate	Slow	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

