

HiFill FR® PBT FR-DE BL511770

 Techmer Polymer Modifiers - *Polybutylene Terephthalate*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Additive	<ul style="list-style-type: none"> Flame Retardant
Features	<ul style="list-style-type: none"> Flame Retardant
Appearance	<ul style="list-style-type: none"> Blue
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.26		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	346000	psi	ASTM D638
Tensile Strength (Yield)	7000	psi	ASTM D638
Tensile Strength (Break)	5000	psi	ASTM D638
Tensile Elongation (Break)	36	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.2	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	460 to 500	°F
Middle Temperature	470 to 510	°F
Front Temperature	480 to 520	°F
Nozzle Temperature	490 to 530	°F
Processing (Melt) Temp	465 to 525	°F
Mold Temperature	125 to 175	°F
Injection Rate	Slow	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow-Moderate	

