

HiFill® PBT GF30 BK

 Techmer Polymer Modifiers - *Polybutylene Terephthalate*
General Information
General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.53		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical			
Nominal Value Unit Test Method			
Tensile Strength (Break)	19500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	28000	psi	ASTM D790
Impact			
Nominal Value Unit Test Method			
Notched Izod Impact (73°F, 0.125 in)	1.9	ft-lb/in	ASTM D256
Thermal			
Nominal Value Unit Test Method			
Deflection Temperature Under Load (66 psi, Unannealed)	428	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	419	°F	ASTM D648
Electrical			
Nominal Value Unit Test Method			
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	520	V/mil	ASTM D149
Flammability			
Nominal Value Unit Test Method			
Flame Rating (0.06 in)	HB		UL 94
Additional Information			
Nominal Value Unit Test Method			
TPCI #	9864111		

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	250	°F
Drying Time	4.0	hr
Rear Temperature	450 to 525	°F
Middle Temperature	450 to 525	°F
Front Temperature	450 to 525	°F
Processing (Melt) Temp	450 to 475	°F
Mold Temperature	150 to 180	°F
Back Pressure	50.0 to 100	psi
Screw Speed	30 to 60	rpm

