

HiFill® TPX-PBT-01022

 Techmer Polymer Modifiers - *Polybutylene Terephthalate*
General Information
General

Material Status	<ul style="list-style-type: none"> Commercial: Active
Availability	<ul style="list-style-type: none"> North America
Filler / Reinforcement	<ul style="list-style-type: none"> Mineral, 25% Filler by Weight
Additive	<ul style="list-style-type: none"> Molybdenum Disulfide Lubricant
Features	<ul style="list-style-type: none"> Lubricated
Appearance	<ul style="list-style-type: none"> Colors Available
Forms	<ul style="list-style-type: none"> Pellets
Processing Method	<ul style="list-style-type: none"> Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.46		ASTM D792
Molding Shrinkage - Flow (0.125 in)	8.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.090	%	ASTM D570
Mechanical			
Tensile Strength (Yield)	6800	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	500000	psi	ASTM D790
Flexural Strength (Yield)	13000	psi	ASTM D790
Impact			
Notched Izod Impact (0.125 in)	1.5	ft·lb/in	ASTM D256
Hardness			
Rockwell Hardness (R-Scale)	112		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	320	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	190	°F	ASTM D648
Electrical			
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	520	V/mil	ASTM D149
Flammability			
Flame Rating (0.06 in)	HB		UL 94

