

**LATILUB 75/4-10T-V0**

 LATI INDUSTRIA TERMOPLASTICI SPA - *Polybutylene Terephthalate*
**General Information**
**Product Description**

Self-lubricating product based on Polybutylene Terephthalate (PBT). PTFE. Flame retardant, UL94 V-0 class, with brominated flame retardants, free of PBB/PBDE and antimony trioxide.

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant • PTFE Lubricant		
Features	• Brominated • Lubricated		
	• Flame Retardant • Self Lubricating		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.45	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>			ISO 294-4
Across Flow : 0.0787 in	1.5 to 1.8	%	
Flow : 0.0787 in	1.5 to 1.8	%	
Water Absorption <sup>3</sup> (Saturation, 73°F)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	377000	psi	ISO 527-1/1
Tensile Stress (Break, 73°F)	5080	psi	ISO 527-2/5
Tensile Strain (Break, 73°F)	2.0	%	ISO 527-2/5
Coefficient of Friction <sup>4</sup>			Internal Method
Dynamic	0.27		
Static	0.23		
Wear Factor <sup>5</sup>	400	10 <sup>-10</sup> in <sup>3</sup> ·min/ft·lb·hr	Internal Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	1.2	ft·lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	14	ft·lb/in <sup>2</sup>	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	284	°F	ISO 75-2/B
Deflection Temperature Under Load (264 psi, Unannealed)	131	°F	ISO 75-2/A
Vicat Softening Temperature	338	°F	ISO 306/B120
CLTE - Flow (86 to 212°F)	6.7E-5	in/in/°F	ISO 11359-2
CLTE - Transverse (86 to 212°F)	6.7E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+12	ohms	ASTM D257
Dielectric Strength (73°F, 0.0787 in, Method A (Short-Time))	480	V/mil	ASTM D149

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 60 MPa

<sup>3</sup> in air

<sup>4</sup> ISO 7148-2 (speed 0.126 m/s, load 10N)

<sup>5</sup> ISO 7148-2 (speed 0.126 m/s, load 10N, path length 13.6km)
