

LONGLITE® PBT 4330G-BKT0

 Chang Chun Plastics Co., Ltd. (CCP Group) - *Polybutylene Terephthalate*
General Information
Product Description

4330G-BKT0 is a 30% glass fiber reinforced and flame-retardant injection-molding grade.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Flame Retardant • Mold Release
Features	• Flame Retardant
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT-GF30 FR(17)<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.68	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.80 to 1.1	%	
Flow	0.30 to 0.50	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	0.040	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	18900	psi	ISO 527-2
Tensile Strain (Break)	1.5	%	ISO 527-2
Flexural Modulus	1.23E+6	psi	ISO 178
Flexural Stress	26100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.6	ft-lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	392	°F	ISO 75-2/A
Melting Temperature ²	437	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength (0.0787 in)	510	V/mil	IEC 60243-1
Comparative Tracking Index (CTI)	PLC 2		UL 746A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	V-0		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.029 in	1760	°F	
0.06 in	1760	°F	
0.12 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.029 in	1560	°F	
0.06 in	1520	°F	
0.12 in	1650	°F	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 284	°F



Drying Time	3.0 to 5.0 hr
Suggested Max Moisture	0.040 %
Processing (Melt) Temp	464 to 518 °F
Mold Temperature	104 to 176 °F

Notes

¹ Typical properties: these are not to be construed as specifications.

² 10°C/min

