

## LONGLITE® PBT 5630F-403R

Chang Chun Plastics Co., Ltd. (CCP Group) - *Polybutylene Terephthalate*

### General Information

#### Product Description

PBT 5630F-403R is a glass fiber/mineral reinforced and flame-retardant injection-molding grade PBT.  
(Halogen and Antimony Free)

#### General

|                        |                       |                   |                 |
|------------------------|-----------------------|-------------------|-----------------|
| Material Status        | • Commercial: Active  |                   |                 |
| Availability           | • Asia Pacific        | • Europe          | • North America |
| Filler / Reinforcement | • Glass Fiber/Mineral |                   |                 |
| Additive               | • Flame Retardant     | • Mold Release    |                 |
| Features               | • Antimony Free       | • Flame Retardant | • Halogen Free  |
| Forms                  | • Pellets             |                   |                 |
| Processing Method      | • Injection Molding   |                   |                 |

### Properties <sup>1</sup>

| Physical                                     | Nominal Value | Unit                  | Test Method |
|----------------------------------------------|---------------|-----------------------|-------------|
| Density                                      | 1.47          | g/cm <sup>3</sup>     | ISO 1183    |
| Molding Shrinkage                            |               |                       | ISO 294-4   |
| Across Flow                                  | 0.80 to 1.2   | %                     |             |
| Flow                                         | 0.20 to 0.50  | %                     |             |
| Water Absorption (Equilibrium, 73°F, 50% RH) | 0.20          | %                     | ISO 62      |
| Mechanical                                   | Nominal Value | Unit                  | Test Method |
| Tensile Stress (Break)                       | 14400         | psi                   | ISO 527-2   |
| Tensile Strain (Break)                       | 2.7           | %                     | ISO 527-2   |
| Flexural Modulus                             | 1.12E+6       | psi                   | ISO 178     |
| Flexural Stress                              | 21800         | psi                   | ISO 178     |
| Impact                                       | Nominal Value | Unit                  | Test Method |
| Charpy Notched Impact Strength (73°F)        | 4.8           | ft·lb/in <sup>2</sup> | ISO 179/1eA |
| Thermal                                      | Nominal Value | Unit                  | Test Method |
| Melting Temperature <sup>2</sup>             | 437           | °F                    | ISO 11357-3 |
| Electrical                                   | Nominal Value | Unit                  | Test Method |
| Surface Resistivity                          | 1.0E+13       | ohms                  | IEC 60093   |
| Volume Resistivity                           | > 1.0E+15     | ohms·cm               | IEC 60093   |
| Comparative Tracking Index                   | 600           | V                     | IEC 60112   |
| Flammability                                 | Nominal Value | Unit                  | Test Method |
| Flame Rating (0.016 in)                      | V-0           |                       | UL 94       |

### Processing Information

| Injection              | Nominal Value | Unit |
|------------------------|---------------|------|
| Drying Temperature     | 248 to 284    | °F   |
| Drying Time            | 3.0 to 5.0    | hr   |
| Suggested Max Moisture | 0.040         | %    |
| Processing (Melt) Temp | 464 to 518    | °F   |
| Mold Temperature       | 104 to 176    | °F   |

