

LONGLITE® PBT 5630F-7035R

Chang Chun Plastics Co., Ltd. (CCP Group) - *Polybutylene Terephthalate*

General Information

Product Description

PBT 5630F-7035R is a glass fiber/mineral reinforced and flame-retardant injection-molding grade PBT.
(Halogen and Antimony Free)

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber\Mineral		
Additive	• Flame Retardant	• Mold Release	
Features	• Antimony Free	• Flame Retardant	• Halogen Free
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.47	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.80 to 1.2	%	
Flow	0.20 to 0.50	%	
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	13800	psi	ISO 527-2
Tensile Strain (Break)	2.2	%	ISO 527-2
Flexural Modulus	1.12E+6	psi	ISO 178
Flexural Stress	21000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.8	ft·lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ²	437	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.016 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 284	°F
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	464 to 518	°F
Mold Temperature	104 to 176	°F

