

TRIBIT® LW1500G15K

Samyang Corporation - Polybutylene Terephthalate

General Information

Product Description

TRIBIT® is a crystalline engineering plastic with excellent processability, chemical resistance, wear resistance, and electrical properties. TRIBIT® has short processing cycle because of rapid crystallization. So it provides good dimensional stability and can be used for automotive or precision parts.

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Uses	• Automotive Applications	• Automotive Interior Parts	
Forms	• Pellets		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.38		ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	16	g/10 min	ASTM D1238
Molding Shrinkage - Flow	2.0E-3 to 0.012	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.080	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	12500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	540000	psi	ASTM D790
Flexural Strength (Yield)	18500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.3	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	338	°F	ASTM D648
CLTE - Flow	1.7E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength	530	V/mil	ASTM D149
Dielectric Constant	3.20		ASTM D150
Dissipation Factor	0.020		ASTM D150
Arc Resistance	150	sec	ASTM D495

Notes

¹ Typical properties: these are not to be construed as specifications.

