

LONGLITE® PBT 7015-104SLR

Chang Chun Plastics Co., Ltd. (CCP Group) - Polybutylene Terephthalate + ASA

General Information
Product Description

PBT/ASA 7015-104SLR is a 15% glass fiber reinforced, hydrolysis resistant, laser markable, low warpage injection molding grade.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 15% Filler by Weight
Additive	• Mold Release
Features	• Hydrolysis Resistant • Laser Markable • Low Warpage
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >(PBT+ASA)-GF15<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.70 to 1.1	%	
Flow	0.20 to 0.50	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	798000	psi	ISO 527-1
Tensile Stress (Break)	13100	psi	ISO 527-2
Tensile Strain (Break)	2.7	%	ISO 527-2
Flexural Modulus	580000	psi	ISO 178
Flexural Stress	18100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.8	ft-lb/in ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ²	437	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+13	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength (0.0787 in)	610	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	HB		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 284	°F
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	464 to 518	°F
Mold Temperature	104 to 176	°F

