

LONGLITE® PBT 7030-134X

 Chang Chun Plastics Co., Ltd. (CCP Group) - *Polybutylene Terephthalate + ASA*
General Information
Product Description

PBT/ASA 7030-134X is a 30% glass fiber reinforced injection molding grade.

General

Material Status	• Commercial: Active
Availability	• Asia Pacific • Europe • North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Mold Release
Features	• Good Mold Release
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >(PBT+ASA)-GF30<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (270°C/2.16 kg)	10	g/10 min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.60 to 1.2	%	
Flow	0.10 to 0.40	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.42E+6	psi	ISO 527-1
Tensile Stress (Break)	18900	psi	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	1.10E+6	psi	ISO 178
Flexural Stress	26800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.8	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	24	ft·lb/in ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ²	437	°F	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength (0.0787 in)	530	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.031 in)	HB		UL 94
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (500°F, 1000 sec ⁻¹)	150	Pa·s	ISO 11443

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248 to 284	°F
Drying Time	3.0 to 5.0	hr
Suggested Max Moisture	0.040	%
Processing (Melt) Temp	464 to 518	°F
Mold Temperature	104 to 176	°F

