

AuroraGuard™ ENV12-NC130

Aurora Material Solutions, LLC - Polycarbonate

General Information

Product Description

Injection Molding Grade, Flame Retardant, RoHS Compliant

NC130 = To Be Assigned 5 Digit Number Indicating Opaque Natural, Black, or Opaque Custom Color.

The ENV12 Series Products Are Available With Mold Release and/or UV Stabilizer.

Contact Enviroplas Regarding UL Recognized Versions Of This Product.

Formerly known as ENVIROPLAS® ENV12-NC130

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Flame Retardant		
Uses	• Electrical/Electronic Applications	• Fluid Handling	• Medical Device Housings
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Natural Color	
	• Colors Available	• Opaque	
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.10		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0E-3 to 3.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9000	psi	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	325000	psi	ASTM D790
Flexural Strength	13200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	12	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	270	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating			Internal Method
0.06 in		V-0	
0.12 in	•	V-0	
	•	5VA	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	230	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	500 to 540	°F
Middle Temperature	520 to 560	°F
Front Temperature	540 to 580	°F
Nozzle Temperature	550 to 600	°F



Mold Temperature	155 to 200 °F
Injection Rate	Moderate-Fast
Back Pressure	50.0 to 100 psi
Screw Speed	40 to 70 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

