

AuroraGuard™ ENV14-NC190

Aurora Material Solutions, LLC - Polycarbonate

General Information

Product Description

Injection Molding Grade, Flame Retardant, Impact-Modified for Increased Toughness, Excellent Low Temperature Impact Resistance, RoHS Compliant
 NC190 = To Be Assigned 5 Digit Number Indicating Natural, Black, or Custom Color.
 The ENV14 Series Products Are Available With Mold Release and/or UV Stabilizer.
 Contact Enviroplas Regarding UL Recognized Versions Of This Product.

Formerly known as ENVIROPLAS® ENV14-NC190

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Flame Retardant		
Features	• Flame Retardant	• Impact Modifier	
	• Good Toughness	• Low Temperature Impact Resistance	
Uses	• Aerospace Applications	• Appliances	• Automotive Applications
RoHS Compliance	• RoHS Compliant		
Appearance	• Black	• Colors Available	• Natural Color
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8800	psi	ASTM D638
Tensile Elongation (Break)	120	%	ASTM D638
Flexural Modulus	325000	psi	ASTM D790
Flexural Strength	12900	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-22°F	9.0	ft·lb/in	
73°F	14	ft·lb/in	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	265	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating			Internal Method
0.06 in	V-0		
0.12 in	5VA		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	230	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	500 to 540	°F
Middle Temperature	520 to 560	°F
Front Temperature	540 to 580	°F



Nozzle Temperature	530 to 570 °F
Mold Temperature	155 to 200 °F
Injection Rate	Moderate-Fast
Back Pressure	50.0 to 100 psi
Screw Speed	40 to 70 rpm

Notes

¹ Typical properties: these are not to be construed as specifications.

