

**ColorFast® FRPC60TFUV**

Americhem - Polycarbonate

## General Information

**Product Description**

Lubricated, low friction, Flame-retarded , UV stabilized injection molding polycarbonate

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Flame Retardant		
Features	• Excellent Colorability	• Flame Retardant	
Uses	• Automotive Applications • Closures • Consumer Applications	• Engineering Parts • Household Goods • Housings	• Industrial Applications • Industrial Parts • Office Automation Equipment
UL File Number	• E178307		
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.23		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	6.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield)	8700	psi	ASTM D638
Tensile Strength <sup>2</sup> (Break)	8500	psi	ASTM D638
Tensile Elongation <sup>2</sup> (Yield)	7.0	%	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	20	%	ASTM D638
Flexural Modulus <sup>2</sup>	330000	psi	ASTM D790
Flexural Strength <sup>2</sup>	13000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	10	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed, 0.250 in)	270	°F	ASTM D648

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	48	hr
Suggested Shot Size	40 to 60	%
Rear Temperature	530 to 580	°F
Middle Temperature	560 to 610	°F
Front Temperature	580 to 620	°F
Nozzle Temperature	560 to 620	°F
Processing (Melt) Temp	580 to 620	°F
Mold Temperature	160 to 200	°F
Back Pressure	50.0 to 100	psi



Screw Speed	40 to 70 rpm
Vent Depth	1.0E-3 to 3.0E-3 in

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 2.0 in/min

