

ColorFast® PC100R

Americhem - Polycarbonate

General Information
Product Description

10 melt standard injection molding grade with release

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Mold Release		
Features	• Excellent Colorability	• Good Mold Release	• Lubricated
Uses	• Automotive Applications	• Engineering Parts	• Industrial Applications
	• Closures	• Household Goods	• Industrial Parts
	• Consumer Applications	• Housings	• Office Automation Equipment
UL File Number	• E178307		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	9000	psi	ASTM D638
Tensile Strength ² (Break)	10000	psi	ASTM D638
Tensile Elongation ² (Yield)	7.0	%	ASTM D638
Tensile Elongation ² (Break)	130	%	ASTM D638
Flexural Modulus ²	340000	psi	ASTM D790
Flexural Strength ²	14000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	15	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed, 0.250 in)	270	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes
¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min
