

ColorFast® PC300

Americhem - Polycarbonate

General Information

Product Description

35 melt superior processing, fast cycling Polycarbonate

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Excellent Colorability		
Uses	• Automotive Applications • Closures • Consumer Applications	• Engineering Parts • Household Goods • Housings	• Industrial Applications • Industrial Parts • Office Automation Equipment
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.19		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	35	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	9400	psi	ASTM D638
Tensile Strength ² (Break)	8700	psi	ASTM D638
Tensile Elongation ² (Yield)	6.0	%	ASTM D638
Tensile Elongation ² (Break)	120	%	ASTM D638
Flexural Modulus ²	340000	psi	ASTM D790
Flexural Strength ²	14000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	10	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	70		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed, 0.250 in)	253	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248	°F
Drying Time	4.0	hr
Rear Temperature	480 to 520	°F
Middle Temperature	510 to 550	°F
Front Temperature	530 to 580	°F
Nozzle Temperature	520 to 580	°F
Processing (Melt) Temp	530 to 605	°F
Mold Temperature	150 to 230	°F
Back Pressure	1400 to 2900	psi

