

ColorFast® XACR200

Americhem - Polycarbonate

General Information
Product Description

Specially formulated impact modified acrylic polymer for extrusion processes

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Excellent Colorability		
Uses	• Automotive Applications	• Engineering Parts	• Industrial Applications
	• Closures	• Household Goods	• Industrial Parts
	• Consumer Applications	• Housings	• Office Automation Equipment
UL File Number	• E178307		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.16		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	1.1	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	6500	psi	ASTM D638
Tensile Elongation ² (Yield)	5.0	%	ASTM D638
Tensile Elongation ² (Break)	40	%	ASTM D638
Flexural Modulus ²	270000	psi	ASTM D790
Flexural Strength ²	8890	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.1	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	45		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed, 0.250 in)	176	°F	ASTM D648

Notes
¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min
