

**Electrafil® PC 04003 MB**

 Techmer Polymer Modifiers - *Polycarbonate*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Features	• Electromagnetic Shielding (EMI)
Appearance	• Colors Available
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.27		ASTM D792
Molding Shrinkage - Flow (0.125 in)	7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	7100	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	380000	psi	ASTM D790
Flexural Strength	12500	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.0	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	265	°F	ASTM D648
CLTE - Flow	3.2E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+2	ohms	ASTM D257
Volume Resistivity	< 1.0E+2	ohms·cm	ASTM D257
Shielding Effectiveness - 30 to 1000 MHz	55	dB	ASTM D4935
Static Decay	< 0.100		FTMS 101B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-1		UL 94

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	575 to 600	°F
Middle Temperature	600 to 630	°F
Front Temperature	590 to 620	°F
Nozzle Temperature	590 to 620	°F
Processing (Melt) Temp	580 to 620	°F
Mold Temperature	160 to 190	°F
Injection Rate	Moderate	
Back Pressure	0.00 to 100	psi

**Injection Notes**

Screw Speed: Medium  
 Recommendations for Molding and Tool Conditions: Well vented mold  
 Moisture Content, as received: Product is packaged at 0.2% or less.

