

ColorRx® PC-1300RX

Americhem - Polycarbonate

General Information
Product Description

PC-1300RX is a medium flow injection molding grade of polycarbonate with good clarity and hydrolysis resistance. It is suitable for healthcare applications and sterilizable by EtO, steam at 121°C, and limited gamma radiation.

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> Africa & Middle East Asia Pacific 	<ul style="list-style-type: none"> Europe Latin America 	<ul style="list-style-type: none"> North America
Features	<ul style="list-style-type: none"> Autoclave Sterilizable Biocompatible E-beam Sterilizable 	<ul style="list-style-type: none"> Ethylene Oxide Sterilizable Excellent Colorability Heat Sterilizable 	<ul style="list-style-type: none"> Radiation Sterilizable Steam Sterilizable
Uses	<ul style="list-style-type: none"> Closures Engineering Parts 	<ul style="list-style-type: none"> Housings Industrial Parts 	<ul style="list-style-type: none"> Medical/Healthcare Applications Surgical Instruments
Agency Ratings	<ul style="list-style-type: none"> ISO 10993 	<ul style="list-style-type: none"> ISO 10993-1 	
Forms	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Injection Molding 		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow	6.0E-3 to 8.0E-3	in/in	ASTM D955
Water Absorption (24 hr, 73°F)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	9300	psi	ASTM D638
Tensile Elongation (Yield)	6.0	%	ASTM D638
Tensile Elongation (Break)	110	%	ASTM D638
Flexural Modulus	335000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	16	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	73		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed, 0.250 in)	277	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.

