

Electrafil® PC 04006 FR BK

Techmer Polymer Modifiers - *Polycarbonate*

General Information

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Stainless Steel Fiber
Features	• Electromagnetic Shielding (EMI) • Flame Retardant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.27		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.5E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	10100	psi	ASTM D638
Tensile Elongation (Yield)	2.0	%	ASTM D638
Flexural Modulus	520000	psi	ASTM D790
Flexural Strength	15100	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	2.0	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	124		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	290	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	280	°F	ASTM D648
CLTE - Flow	1.8E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0 to 1.0E+3	ohms	ASTM D257
Volume Resistivity	1.0 to 1.0E+3	ohms·cm	ASTM D257
Shielding Effectiveness	50	dB	ASTM D4935
Static Decay	< 0.1	sec	FTMS 101B
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	575 to 600	°F
Middle Temperature	600 to 630	°F
Front Temperature	590 to 620	°F
Nozzle Temperature	590 to 620	°F
Processing (Melt) Temp	580 to 620	°F
Mold Temperature	160 to 190	°F
Injection Rate	Moderate	



Back Pressure	0.00 to 100 psi
Injection Notes	
Screw Speed: Medium	
Recommendations for Molding and Tool Conditions: Well vented mold	
Moisture Content, as received: Product is packaged at 0.2% or less.	
Notes	
¹ Typical properties: these are not to be construed as specifications.	

