

**HiFill FR® PC CF30 FR BK**

 Techmer Polymer Modifiers - *Polycarbonate*
**General Information**
**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant
Appearance	• Black
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.28		ASTM D792
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Modulus	1.77E+6	psi	ASTM D638
Tensile Strength (Yield)	19500	psi	ASTM D638
Tensile Strength (Break)	19500	psi	ASTM D638
Tensile Elongation (Break)	2.3	%	ASTM D638
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (0.125 in)	1.4	ft·lb/in	ASTM D256
<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating (0.06 in)	V-0		UL 94

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	500 to 540	°F
Middle Temperature	510 to 550	°F
Front Temperature	520 to 560	°F
Nozzle Temperature	530 to 570	°F
Processing (Melt) Temp	510 to 565	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

