

**Electrafil® PC MCF/GB 1525 BK001**

 Techmer Polymer Modifiers - *Polycarbonate*
**General Information**
**General**

Material Status	<ul style="list-style-type: none"> <li>Commercial: Active</li> </ul>
Availability	<ul style="list-style-type: none"> <li>North America</li> </ul>
Appearance	<ul style="list-style-type: none"> <li>Black</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.44		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13900	psi	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 to 1.0E+6	ohms	ASTM D257

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	460 to 500	°F
Middle Temperature	470 to 510	°F
Front Temperature	480 to 520	°F
Nozzle Temperature	490 to 530	°F
Processing (Melt) Temp	465 to 525	°F
Mold Temperature	125 to 175	°F
Injection Rate	Slow	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow-Moderate	

**Notes**
<sup>1</sup> Typical properties: these are not to be construed as specifications.
