

## HiFill FR® PC FR IM

Techmer Polymer Modifiers - *Polycarbonate*

### General Information

#### General

|                   |                                            |
|-------------------|--------------------------------------------|
| Material Status   | • Commercial: Active                       |
| Availability      | • North America                            |
| Additive          | • Impact Modifier                          |
| Features          | • Flame Retardant • High Impact Resistance |
| Appearance        | • Colors Available • Colors Available      |
| Forms             | • Pellets                                  |
| Processing Method | • Injection Molding                        |

### Properties <sup>1</sup>

| Physical                                                | Nominal Value | Unit     | Test Method |
|---------------------------------------------------------|---------------|----------|-------------|
| Density / Specific Gravity                              | 1.19          |          | ASTM D792   |
| Molding Shrinkage - Flow (0.125 in)                     | 5.0E-3        | in/in    | ASTM D955   |
| Water Absorption (24 hr)                                | 0.13          | %        | ASTM D570   |
| Mechanical                                              | Nominal Value | Unit     | Test Method |
| Tensile Strength (Yield)                                | 8000          | psi      | ASTM D638   |
| Tensile Elongation (Yield)                              | 90            | %        | ASTM D638   |
| Flexural Modulus                                        | 33000         | psi      | ASTM D790   |
| Flexural Strength                                       | 12000         | psi      | ASTM D790   |
| Impact                                                  | Nominal Value | Unit     | Test Method |
| Notched Izod Impact (73°F, 0.125 in)                    | 8.0           | ft-lb/in | ASTM D256   |
| Hardness                                                | Nominal Value | Unit     | Test Method |
| Rockwell Hardness (R-Scale)                             | 114           |          | ASTM D785   |
| Thermal                                                 | Nominal Value | Unit     | Test Method |
| Deflection Temperature Under Load (264 psi, Unannealed) | 240           | °F       | ASTM D648   |
| CLTE - Flow                                             | 3.7E-5        | in/in/°F | ASTM D696   |
| Electrical                                              | Nominal Value | Unit     | Test Method |
| Surface Resistivity                                     | 1.0E+14       | ohms     | ASTM D257   |
| Volume Resistivity                                      | 1.0E+15       | ohms·cm  | ASTM D257   |
| Dielectric Strength (Method A (Short-Time))             | 440           | V/mil    | ASTM D149   |
| Flammability                                            | Nominal Value | Unit     | Test Method |
| Flame Rating (0.12 in)                                  | V-0           |          | UL 94       |

### Processing Information

| Injection              | Nominal Value | Unit |
|------------------------|---------------|------|
| Drying Temperature     | 250           | °F   |
| Drying Time            | 4.0           | hr   |
| Rear Temperature       | 540 to 560    | °F   |
| Middle Temperature     | 540 to 560    | °F   |
| Front Temperature      | 540 to 560    | °F   |
| Processing (Melt) Temp | 510 to 560    | °F   |
| Mold Temperature       | 180 to 250    | °F   |
| Back Pressure          | 50.0 to 100   | psi  |
| Screw Speed            | 30 to 60      | rpm  |

