

InLube® PCGF20TF15VHFUV

Americhem - Polycarbonate

General Information

Product Description

20% GLASS FIBER REINFORCED, 15% PTFE LUBRICATED, VERY HIGH FLOW, UV STABILIZED, POLYCARBONATE

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Additive	• PTFE Lubricant: 15%	• UV Stabilizer	
Features	• Chemical Resistant • Filled • Good Dimensional Stability • Good Mold Release	• High Flow • High Stiffness • High Strength • Low Friction	• Lubricated • UV Stabilized • Wear Resistant
Uses	• Automotive Applications • Closures • Connectors • Consumer Applications	• Electrical/Electronic Applications • Engineering Parts • Household Goods • Housings	• Industrial Applications • Industrial Parts • Office Automation Equipment • Outdoor Applications
Forms	• Pellets		
Processing Method	• Injection Molding		

 Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.46		ASTM D792
Molding Shrinkage - Flow	1.0E-3 to 3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.060	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.05E+6	psi	ASTM D638
Tensile Strength	14500	psi	ASTM D638
Tensile Elongation (Yield)	3.0 to 5.0	%	ASTM D638
Flexural Modulus	850000	psi	ASTM D790
Flexural Strength	22000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	2.1	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	16	ft-lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	275	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Processing (Melt) Temp	560 to 600	°F
Mold Temperature	180 to 225	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

