

**InLube® PCTF3SI2HFMRMD**

Americhem - Polycarbonate

**General Information**
**Product Description**

3% PTFE/2% SILICONE LUBRICATED, HIGH FLOW, MOLD RELEASE POLYCARBONATE, LOCKED MEDICAL FORMULA

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Additive	• Mold Release	• PTFE Lubricant: 3%	• Silicone Lubricant: 2%
Features	• Autoclave Sterilizable • Chemical Resistant • E-beam Sterilizable • Ethylene Oxide Sterilizable	• Good Mold Release • Heat Sterilizable • High Flow • Low Friction	• Lubricated • Radiation Sterilizable • Steam Sterilizable • Wear Resistant
Uses	• Closures • Connectors • Electrical/Electronic Applications	• Engineering Parts • Housings • Industrial Parts	• Medical/Healthcare Applications • Surgical Instruments
Forms	• Pellets		
Processing Method	• Injection Molding		

**Properties <sup>1</sup>**

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Molding Shrinkage - Flow	5.0E-3 to 8.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	300000	psi	ASTM D638
Tensile Strength	8000	psi	ASTM D638
Tensile Elongation (Yield)	> 10	%	ASTM D638
Flexural Modulus	320000	psi	ASTM D790
Flexural Strength	12000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	6.5	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	No Break		ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	275	°F	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.12 in)	HB		UL 94

**Processing Information**

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Processing (Melt) Temp	580 to 620	°F
Mold Temperature	180 to 240	°F
Back Pressure	50.0 to 100	psi
Screw Speed	40 to 70	rpm

